



DESCRIPTION

Quick Primer Glass is a blend of reactive polyurethane oligomers dissolved in organic solvents.

AREAS OF USE

Can be used in the automotive industry to improve the adhesion of polyurethane sealants on screen printed ceramic glass.

TECHNICAL DATA

Color	Black
Viscosity	100 mL DIN cup, $\varnothing = 4$ mm: 12 to 15 s
Density at 20°C	0.90 ± 0.05
Conventional Solids content	28.5 ± 1.5 %.
Recommended temperatura	5 to 25 °C
Drying time	20 °C : 10 to 15 min

APPLICATION METHOD

Substrate preparation:

- The substrate to be coated must be free of dry dust, flat and free of any traces of grease or other contaminants that could affect the bonding performance.
- Degrease the ceramic screen printing with a solvent such as acetone.
- When using solvents, extinguish all ignition sources and carefully follow the safety and handling instructions given by the manufacturer.

Directions for use:

- Shake the product well before use. Seal container tightly immediately after use.
- Any contact with moisture will cause the primer to cure. For this reason, the product should be used within 24 hours after opening the bottle.
- After drying, apply the sealer within one hour, proceed according to the instructions on its data sheet. Shake well before use.
- Close tightly immediately after use

- Apply an even coat to achieve a lint-free finish.
- Once dry, apply the glue within one hour.

SAFETY INFORMATION

See Safety Data Sheet.

WARNINGS

- During the first 5 minutes after application, it is possible to clean with hydrocarbons.
- 12 months in unopened original packaging stored in a dry place between 0 and 25 ° C .24 h after opening.

AVAILABLE PACKAGING

Code	Description	Packaging
5002-001109	QUICK PRIMER GLASS	30ML

*For more information about our products or means of application, please visit our website www.carrepairsystem.eu or send us an e-mail to info@carrepairsystem.eu

The technical information and instructions provided in this sheet are based on our own working experience. The company ensures the quality of the product. However, as the uses terms and conditions are out of our control, we decline any responsibility as the final result is concerned.